



## PATENT ABSTRACTS OF JAPAN

(11) Publication number: **06254414 A**(43) Date of publication of application: **13.09.94**

(51) Int. Cl.

**B01J 37/03****B01J 23/80****C07B 61/00****C07C 29/153****C07C 31/04**(21) Application number: **05041197**(22) Date of filing: **02.03.93**(71) Applicant: **mitsubishi gas chem co inc**

(72) Inventor: **NAKAMURA TADASHI**  
**TSUJI KINYA**  
**OBATA YORIKO**  
**WATANABE TOSHIYASU**  
**TANAKA FUMIO**

**(54) PREPARATION OF CATALYST****(57) Abstract:**

**PURPOSE:** To improve catalytic performance by adding a precursor component selected from among hydroxy acid such as silicon, boron or chromium and its salts to each precursor component of copper oxide, zinc oxide, zirconium oxide and/or aluminum oxide, in a methanol synthesis catalyst.

**CONSTITUTION:** Each precursor component of copper oxide and zinc oxide, and each precursor component of

zirconium and/or aluminum oxide are used as ingredients, and at least, one type of each precursor component selected from hydroxy acid such as silicon, boron, chromium, vanadium, magnesium or phosphorus and its salts, if necessary. In addition, 30wt.% of CO<sub>2</sub> as a reduced weight is added. Further, the content of zirconium and/or aluminum is 80wt.% max in terms of an oxide. Finally CO<sub>2</sub> is allowed to be added to the precursor by using a sedimentation agent containing a carbonic acid product.

COPYRIGHT: (C)1994,JPO&amp;Japio

# Bibliographic data

## Document JP000006254414AA (Pages: 1)

Bibliographic data Document JP000006254414AA (Pages: 1)

Criterion	Field	Contents
Title	TI	[ ] PREPARATION OF CATALYST
Applicant	PA	MITSUBISHI GAS CHEM CO INC
Inventor	IN	NAKAMURA TADASHI ; TSUJI KINYA ; OBATA YORIKO ; WATANABE TOSHIYASU ; TANAKA FUMIO
Application date	AD	02.03.1993
Application number	AN	4119793
Country of application	AC	JP
Publication date	PUB	13.09.1994
Priority data	PRC PRN PRD	
IPC main class	ICM	<u>B01J 37/03</u>
IPC secondary class	ICS	<u>B01J 23/80</u> <u>C07B 61/00</u> <u>C07C 29/153</u> <u>C07C 31/04</u>
IPC additional class	ICA	
IPC index class	ICI	
MCD main class	MCM	
MCD secondary class	MCS	<u>B01J 23/76</u> (2006.01) C, , I, 20051206, R, M, EP <u>B01J 23/80</u> (2006.01) A, , I, 20051206, R, M, EP <u>B01J 37/00</u> (2006.01) C, , I, 20051206, R, M, EP <u>B01J 37/03</u> (2006.01) A, , I, 20051206, R, M, EP <u>C07B 61/00</u> (2006.01) A, , I, 20051206, R, M, EP <u>C07C 29/00</u> (2006.01) C, , I, 20051206, R, M, EP <u>C07C 29/153</u> (2006.01) A, , I, 20051206, R, M, EP <u>C07C 31/00</u> (2006.01) C, , I, 20051206, R, M, EP <u>C07C 31/04</u> (2006.01) A, , I, 20051206, R, M, EP
MCD additional	MCA	

class

[ ]

PURPOSE: To improve catalytic performance by adding a precursor component selected from among hydroxy acid such as silicon, boron or chromium and its salts to each precursor component of copper oxide, zinc oxide, zirconium oxide and/or aluminum oxide, in a methanol synthesis catalyst.

Abstract

AB

CONSTITUTION: Each precursor component of copper oxide and zinc oxide, and each precursor component of zirconium and/or aluminum oxide are used as ingredients, and at least, one type of each precursor component selected from hydroxy acid such as silicon, boron, chromium, vanadium, magnesium or phosphorus and its salts, if necessary. In addition, 30wt.% of CO<sub>2</sub> as a reduced weight is added. Further, the content of zirconium and/or aluminum is 80wt.% max in terms of an oxide. Finally CO<sub>2</sub> is allowed to be added to the precursor by using a sedimentation agent containing a carbonic acid product.

COPYRIGHT: (C)1994,JPO&Japio

Information on correction KORRINF

Cited documents CT

Cited non-patent literature CTNP

[PDF display](#)

© DPMA 2005



[\[Top\]](#)

Patent Family


Result list: Hits: 1 (Total hits: 1) [Download result list](#)

No. Publication number 

Title

Display PDF Patent family search

1 [JP000006254414AA](#)

[ ] PREPARATION OF CATALYST 

[JP000006254414AA](#)